



Technical Data Sheet

Property	Values	Unit	Test method
Peel strength	> 2,5	N/15 mm	DIN EN 60 249-1
Tensile strength* MD TD	> 130 > 1160	N/ mm ²	DIN EN ISO 527-3
Elongation to break* MD TD	> 120 > 80	%	DIN EN ISO 527-3
Maximum operating temperature	110	°C	
Heat resistant (short time)	150	°C	
Shrinkage # after etch 30 min/ 150 °C MD TD	< 0,4 < 0,2	%	DIN EN 60 249-1
Surface resistance R _o min.	10 ¹¹	Ω	ASTM-D 257-83

* for Base Material 9 μ Al/ 50 μ PET

The foregoing data have been obtained using standard test procedures on defined specimens. The results should therefore only be regarded as a general guide to material properties and not as design data